



SDP
ADVANCED POLYMER PRODUCTS

SDP Inc.
410-130 Bridgeland Ave.,
Toronto, Ontario,
Canada M6A 1Z4

Toll Free : 866-747-4035
Fax : 866-840-3857
info@sdp-products.com • sdp-products.com



PALISADETM SA-HT

SELF ADHERED UNDERLAYMENT

TECHNICAL DATA

TECHNICAL DATA PROPERTY	TEST METHOD	PALISADE TM SA-HT TYPICAL VALUE
Color	-	KOOL BLUE TM
Top Surface	-	STRONGHOLD TM Anti-Skid Technology: Polymer
Bottom Release Liner	-	Silicone Split Release Poly
Permeability	ASTM E96-00	0.01 perms
Nominal Thickness	ASTM D1777	40 mil (1 mm)
Nail Sealability	ASTM D1970	Pass
Lap Sealability	ASTM D1970	Pass
Tensile Strength	ASTM D226	121 lbf/in. (21kN/m)
Tear Strength	ASTM D4523	160 lbf/in. (28 kN/m)
Elongation	ASTM D2523-00	16%
Low Temperature Flexibility	ASTM D1970	-22° F (-30° C) - Pass
Adhesion to Plywood	ASTM D1876	55 lbf/in.: 75° F (9.6 kN/m: 24° C)
Adhesion to Plywood	ASTM D1876	23 lbf/in.: 40° F (4 kN/m: 4.4° C)
UV Exposure	ASTM G90	6 months
Temperature Range	ASTM D1970	LT: 15° F (-9° C) to HT: 250° F (121° C)
Dimensions	-	36 in. x 66.7 ft. (91.4 cm x 20.3 m)
Square/Roll	-	2
Roll Weight	-	45 lbs. (21 kg)
Rolls/Pallet	-	30

This product is manufactured in accordance with national standards which allow for non-critical variances in weights and measurements.